

### **GEL 12-150**



#### **FEATURES**



Compact size ideal for any type of use.




High performance due to its deep discharge life cycle.



Designed for photovoltaic installations.


#### **DIMENSIONS**







 $\ensuremath{^*}$  Stainless steel connection inox, included in packaging.







#### **GEL BATTERY** 12V 150 AH

#### **GEL SERIES BATTERY**

The GEL series batteries incorporate the new CCDR continuous lamination stamped plate technology, which allows them to withstand deep cyclic charge and discharge applications. The batteries use colloidal or foamed silica gel that immobilises the electrolyte, which further enhances the cycling stability and eliminates stratification.

Gel series batteries are the special design batteries with 15 years floating design life at  $20^{\circ}$ C. Meet with IEC, BS, JIS and Eurobat standards.

# TENSIE WITH CONTROL OF THE CONTROL

#### **APPLICATION**

- Emergency power system.
- Communication equipment.
- Telecommunications systems.
- Uninterruptible power supplies.
- Electric wheelchairs.
- Electric toys, cars and wheelchairs.
- Power tools.
- Golf carts and buggies.
- Marine equipment.
- Medical equipment.
- Solar and wind power system.

#### **GENERAL FEATURES**

- Safety sealing.
- Non-spillable technology.
- High power density.
- Excellent deep discharge recovery.
- Thick plates and highly active materials.
- Longer life and low self-discharge design.

#### **TECHNICAL SPECIFICATIONS**

	Nominal Voltage Rated Capacity (100 Hours)				12 V 150 Ah				
BATTERY MODEL									
	Cells per battery				6				
DIMENSIONS	Length		Width		Height		Tot	Total Height	
DIMENSIONS	407 mm		174 mm		215 mm		2	223 mm	
APPROXIMATE WEIGHT	36.6 kg ± 3%								
CAPACITY @ 25ºC	10 hours		5 hours		3 hours			1 hour	
	120 Ah		96 Ah		87 Ah			72 Ah	
MAXIMUM DISCHARGE CURRENT	1200 A (5 sec.)								
MAXIMUN CHARGE CURRENT	36 A								
INTERNAL RESISTANCE	Fully charged at 25°C: Approx. 4,4 mΩ								
CAPACITY VS TEMPERATURE	40°C		25°C		0°C			-15°C	
	102%		100%		85%			65%	
SELF DISCHARGE @ 25°C	After 3 months in storage				After 6 meses		Afte	After 12 meses	
	91%					82%		64%	
CHARGE METHOD @ 25ºC	Cycle Use				Float Use				
CHARGE METHOD & 25-C	14,30 - 14,60 V				13,60- 13,80 V				
CONSTRUCTION	Container	Electrolyte	Separators	Posi	itive	Negative	Valve	Terminal	
	ABS (UL94-HB) / Flame retardant ABS (UL94-V0)	Sulfuric acid thixotropic gel	Macromolecule polymer	Lead dioxide		Lead	EPDR	Copper	

#### **BATTERY DISCHARGE TABLE**

CONSTANT CURRENT(A) AND ONSTANTE POWER (W) DISCHARGE TABLE AT 25°C										
F.V / TIME		10 mins	15 mins	30 mins	1 hr	3 hrs	5 hrs	10hrs	20 hrs	
1.60	A	190.00	153.30	103.00	54.00	23.10	14.90	9.50	5.10	
	W	338.00	273.50	183.83	97.16	42.90	28.13	18.18	9.88	
1.70	А	171.00	144.00	98.00	51.00	22.50	14.60	9.30	5.00	
	W	318.83	268.83	183.50	95.66	42.50	28.10	18.15	9.68	
1.75	A	153.00	126.00	92.00	49.00	22.00	14.40	9.10	5.00	
	W	290.66	239.83	176.00	94.83	42.50	28.10	17.93	9.65	
1.80	Α	144.00	117.00	85.00	48.00	21.40	14.00	9.00	4.90	
	w	277.66	225.00	163.33	92.16	42.08	27.66	17.83	9.65	
1.85	А	135.00	108.00	76.00	46.00	20.70	13.70	8.60	4.60	
	w	261.16	209.83	147.50	90.00	40.98	27.16	17.20	9.27	





## Tens/te

**USE IN FLOTATION**: The battery is connected to the charger continuously, maintaining the charge at 100%, ready for discharge at specific times. This is the case of alarms, UPS systems, backup systems, telecommunications backup.

**USE IN CYCLES**: The battery is charged and discharged, repeating this cycle regularly. This is the case for residential photovoltaic installations (day/night), electric cars and in applications that are consumed when no load is available. The starting of combustion engines would be an application that combines both types of use.

