

## **GEL 12-150**



## **FEATURES**



Compact size ideal for any type of use.




High performance due to its deep discharge life cycle.



Designed for photovoltaic installations.


## **DIMENSIONS**











Official sponsor of





## **GEL BATTERY** 12V 150 AH

## **GEL SERIES BATTERY**

The GEL series batteries incorporate the new CCDR continuous lamination stamped plate technology, which allows them to withstand deep cyclic charge and discharge applications. The batteries use colloidal or foamed silica gel that immobilises the electrolyte, which further enhances the cycling stability and eliminates stratification.

Gel series batteries are the special design batteries with 15 years floating design life at  $20^{\circ}$ C. Meet with IEC, BS, JIS and Eurobat standards.

## APPLICATION

- Emergency power system.
- Communication equipment.
- Telecommunications systems.
- Uninterruptible power supplies.
- Electric wheelchairs.
- Electric toys, cars and wheelchairs.
- Power tools.
- Golf carts and buggies.
- Marine equipment.
- Medical equipment.
- Solar and wind power system.



## **GENERAL FEATURES**

- Safety sealing.
- Non-spillable technology.
- High power density.
- Excellent deep discharge recovery.
- Thick plates and highly active materials.
- Longer life and low self-discharge design.

#### **TECHNICAL SPECIFICATIONS**

BATTERY MODEL	Nomina	l Voltage	12 V				
	Rated Capaci	ty (100 Hours)	150 Ah				
	Cells pe	r battery	6				
DIMENSIONS	Length	Width	Height	Total Height			
DIMENSIONS	407 mm	174 mm	215 mm	223 mm			
APPROXIMATE WEIGHT	36.6 kg ± 3%						
CAPACITY @ 25ºC	10 hours	5 hours	3 hours	1 hour			
CAPACITY @ 25=C	120 Ah	96 Ah	87 Ah	72 Ah			
MAXIMUM DISCHARGE CURRENT	1200 A (5 sec.)						
MAXIMUN CHARGE CURRENT	36 A						
INTERNAL RESISTANCE	Fully charged at $25^{\circ}$ C: Approx. 4,4 m $\Omega$						
CADACITY VC TEAADED ATLIBE	40°C	25°C	0°C	-15°C			
CAPACITY VS TEMPERATURE	102%	100%	85%	65%			
SELE DISCHARCE & 3ERC	After 3 mont	ths in storage	After 6 meses	After 12 meses			
SELF DISCHARGE @ 25ºC	93	1%	82%	64%			
CHARGE METHOD @ 25°C	Cycle Use		Float Use				
0.m.no2 m2.mo5 @ 25 c	14,30 -	14,60 V	13,60- 13,80 V				

#### **BATTERY DISCHARGE TABLE**

CONSTANT CURRENT(A) AND ONSTANTE POWER (W) DISCHARGE TABLE AT 25°C											
F.V / TIME		10 mins	15 mins	30 mins	1 hr	3 hrs	5 hrs	10hrs	20 hrs		
1.60	A	190.00	153.30	103.00	54.00	23.10	14.90	9.50	5.10		
	W	338.00	273.50	183.83	97.16	42.90	28.13	18.18	9.88		
1.70	Α	171.00	144.00	98.00	51.00	22.50	14.60	9.30	5.00		
	W	318.83	268.83	183.50	95.66	42.50	28.10	18.15	9.68		
1.75	A	153.00	126.00	92.00	49.00	22.00	14.40	9.10	5.00		
	W	290.66	239.83	176.00	94.83	42.50	28.10	17.93	9.65		
1.80	A	144.00	117.00	85.00	48.00	21.40	14.00	9.00	4.90		
	W	277.66	225.00	163.33	92.16	42.08	27.66	17.83	9.65		
1.85	Α	135.00	108.00	76.00	46.00	20.70	13.70	8.60	4.60		
	W	261.16	209.83	147.50	90.00	40.98	27.16	17.20	9.27		





# Tens/te

**USE IN FLOTATION**: The battery is connected to the charger continuously, maintaining the charge at 100%, ready for discharge at specific times. This is the case of alarms, UPS systems, backup systems, telecommunications backup.

**USE IN CYCLES**: The battery is charged and discharged, repeating this cycle regularly. This is the case for residential photovoltaic installations (day/night), electric cars and in applications that are consumed when no load is available. The starting of combustion engines would be an application that combines both types of use.

