

GEL 12-40

FEATURES




Compact size ideal for any type of use.

High performance due to its deep discharge life cycle.

Designed for photovoltaic installations.


DIMENSIONS





*Stainless steel connection inox, included in packaging.

motogn







GEL 12-40

GEL BATTERY 12V 40 AH

GEL SERIES BATTERY

The GEL series batteries incorporate the new CCDR continuous lamination stamped plate technology, which allows them to withstand deep cyclic charge and discharge applications. The batteries use colloidal or foamed silica gel that immobilises the electrolyte, which further enhances the cycling stability and eliminates stratification.

Gel series batteries are the special design batteries with 15 years floating design life at 20 $^\circ$ C. Meet with IEC, BS, JIS and Eurobat standards.

APPLICATION

- Emergency power system.
- Communication equipment.
- Telecommunications systems.
- Uninterruptible power supplies.
 Electric wheelchairs
- Electric wheelchairs.
- Electric toys, cars and wheelchairs.
- Power tools.
- Golf carts and buggies.
- Marine equipment.
- Medical equipment.
- Solar and wind power system.



GENERAL FEATURES

- Safety sealing.
- Non-spillable technology.
- High power density.
- Excellent deep discharge recovery.
- Thick plates and highly active materials.
- Longer life and low self-discharge design.

TECHNICAL SPECIFICATIONS

	Nomina	I Voltage	12 V					
BATTERY MODEL	Rated capacity	(100 hour rate)	40 Ah					
	Cells pe	r battery	6					
	Length	Width	Height	Total Height				
DIMENSIONS	197 mm	165 mm	174 mm	175 mm				
APPROXIMATE WEIGHT	13,45 kg ± 3%							
	10 hours	5 hours	3 hours	1 hour				
CAPACITY @ 25°C	40 Ah	32 Ah	30Ah	24 Ah				
MAXIMUM DISCHARGE CURRENT	380 A (5 sec.)							
MAXIMUN CHARGE CURRENT	12 A							
INTERNAL RESISTANCE	Fully charged at 25°C: Approx 5.9 mΩ							
	40°C	25°C	0°C	-15°C				
CAPACITY VS TEMPERATURE	102%	100%	85%	65%				
	After 3 mon	ths in storage	After 6 months in storage	After 12 months in storage				
SELF DISCHARGE @ 25°C	9:	1%	82%	64%				
CHARGE METHOD @ 25ºC	Cycle Use		Float Use					
	14.4-	15.0V	13,50- 13,80 V					

BATTERY DISCHARGE TABLE


CONSTANT CURRENT(A) AND ONSTANTE POWER (W) DISCHARGE TABLE AT 25°C											
F.V / TIME		10 mins	15 mins	30 min	1 hr	3 hrs	5 hrs	10hrs	20 hrs		
11.1	A	60.0	48.0	33.6	20.4	9.2	6.10	3.80	2.27		
	w	697.0	560.0	393.0	240.0	109.0	73.00	45.90	4.40		
10.80	A	64.0	52.0	37.6	21.1	9.5	6.20	4.00	2.50		
	w	740.0	600.0	436.0	246.0	112.0	74.00	48.00	4.80		
10.50	A	68.00	56.0	40.80	21.8	9.8	6.40	4.04	2.20		
	w	775.0	640.0	470.0	253.0	114.0	75.00	48.00	4.30		
10.20	A	76.0	64.0	43.6	22.6	10.0	6.50	4.12	2.16		
	w	850.0	717.0	489.0	255.0	116.0	76.00	48.00	4.28		
9.60	A	84.0	68.0	45.6	24.0	10.3	6.60	4.20	2.04		
	w	901.0	730.0	490.0	259.0	114.0	75.00	49.00	4.11		







USE IN FLOTATION: The battery is connected to the charger continuously, maintaining the charge at 100%, ready for discharge at specific times. This is the case of alarms, UPS systems, backup systems, telecommunications backup.

USE IN CYCLES: The battery is charged and discharged, repeating this cycle regularly. This is the case for residential photovoltaic installations (day/night), electric cars and in applications that are consumed when no load is available. The starting of combustion engines would be an application that combines both types of use.





Tenste





Self-Discharge Characteristics with Temperature






120 100 80 % Capactiy 60 50% DOD 30% DOD 100% DOD 40 20 0 200 400 600 800 1000 1200 1400 1600 1800 2000

Cycle life in relation to Depth of Discharge

Number of charge-discharge cycles

Discharge Characteristics 25ºC (77ºF)



Voltage Charge and Temperature

